

### Information

Compressibility, softness and durability allow BF-1000 to adapt to various environments, making it an ideal choice for sealing outdoor enclosures, protecting electronics from shock and heat, and providing cushioning or vibration isolation for various applications. BISCO® Silicones are available in various thicknesses and manufactured in roll form to allow fabricators to easily convert the material to the proper dimensions.

### Features and benefits

- Excellent memory and low stress relaxation reduces maintenance costs associated with gasket failures due to compression set and softening.
- Softness allow designers to use less force to seal enclosures and still protect their device from the environment.
- High compressibility allows material to conform to variable width gaps and awkward shapes, thereby allowing engineers more design flexibility.
- Resistance to ultraviolet light, ozone, extreme temperatures, and flame enables consistent performance in all environments.

### Applications

- Environmental seals to protect against penetration of dust, moisture, air, or light within outdoor enclosures such as lighting fixtures, HVAC units, and electronic cabinets.
- Vibration isolation in electronic components and transportation vehicles.
- Fire retardent thermal insulation

### Installation

- Available with a pressure-sensitive adhesive on one or two sides to allow easy application to a variety of surfaces.

### Physical

PROPERTY	TEST METHOD	TYPICAL VALUE
Colour		Grey* and white
Thickness inches (mm) <b>Tolerance</b>		0.062 - 1.00 (1.6 - 25.4) <b>see below</b>
Standard width inches (mm)		36 (914)
Density, lb.ft³ (kg/m³)	ASTM D 1056	13 (208)
Compression force deflection psi (kPa)	Force measured @ 25% deflection ASTM D 1056	3 (20.7)
Compression set % max	ASTM D 1056 Test D @ 158°F (70°C), 22hrs ASTM D 1056 Test D @ 212°F (100°C), 22hrs	< 1 < 5
Tensile strength, psi (kPa)	ASTM D 412	35 (241)
Elongation %	ASTM D 412	90

\*Grey colour is standard in 0.062 (1.9mm), 0.250 (6.4mm) and 0.500 (12.7mm) thicknesses.

### Flammability & Outgassing

PROPERTY	TEST METHOD	TYPICAL VALUE
Flame resistance	UL 94	Listed V-0 and HF-1
Flame spread index (L <sub>s</sub> )	ASTM E 162	< 35
Smoke Density (D <sub>s</sub> )	ASTM E 662 Tested @ 4.0 minutes Tested @ 1.5 minutes	< 50 < 20
Toxic gas emissions rating	SMP-800C & BSS 7239	Pass

### Environmental Properties

PROPERTY	TEST METHOD	TYPICAL VALUE
Water absorption	Internal: 24hrs @ room temp	3.50 %
UV resistance	SAE J- 1960	No degradation
Ozone effect rating	ASTM D 1171	0 (no cracks)
Corrosion resistance	AMS - 3568	Pass
Meets requirements of FDA CFR 177.2600 for Food Contact		BF-1000 white
Other specifications available	BMS 1-68	

### Electrical & Thermal Properties

PROPERTY	TEST METHOD	TYPICAL VALUE
Dielectric constant	ASTM D 150	1.34
Dielectric strength	ASTM D 149, volts/mil	89
Dry arc resistance	ASTM D 495, seconds	90
Volume resistivity, Ohm - cm	ASTM D 257	10 <sup>14</sup>
Thermal conductivity, BTU in/hr/ft <sup>2</sup> /°F (w/m °K)	ASTM C 518	0.39 (0.06)

### Temperature Resistance

PROPERTY	TEST METHOD	TYPICAL VALUE
Low temperature flex at -67°F (-55°C)	ASTM D 1056	Pass
Recommended temperature °F (°C)	SAE J-2236	-67 to 392 (-55 to 200)
Recommended intermittent high temperature use °F (°C)	Internal	482 (250)

STANDARD THICKNESS		TOLERANCE (INCHES)	
INCHES	MM		
1/16	0.062	1.57	± 0.016
3/32	0.094	2.39	± 0.020
1/8	0.125	3.18	± 0.025
3/16	0.188	4.76	± 0.030
1/4	0.250	6.35	± 0.040
3/8	0.375	9.53	± 0.060
1/2	0.500	12.70	± 0.050
3/4	0.750	19.05	± 0.090
1	1.000	25.40	± 0.090

The information and data contained herein is believed to be accurate and reliable. However it is the user's responsibility to determine suitability for use. C B Frost & Co makes no warranties concerning fitness or suitability of its products for a particular use or purpose. C B Frost & Co reserve the right to alter the material specification at any time, without prior notice.

#### Notes

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values are a representation of an average value for the population of the property. For specification values contact Rogers Corporation.

**t** +44 (0) 121 773 8494  
**f** +44 (0) 121 772 3584  
**w** www.cb frost-rubber.com  
**e** info@cb frost-rubber.com  
**t** twitter.com/cbfrost