

Grade: CBF-812
Colour: White/Black
Density: 100-120kgs/m³
Width: 1000mm – 1400mm
Thickness (mm): 2,3,4,5,6,8,10,12,15,18,20
Roll Length: 25 – 130 meters according to the thickness

PROPERTY	UNIT	VALUE	TEST METHOD
Denisty	kgs/m ³	100-125	
Tensile Strength	kpa	>150	DIN 53571
Elongation at break	%	>120	DIN 53571
Tear Strength	N/mm	>0.7	DIN 53515
Compression Set	%	<20	DIN 53572
Compression Deflection	Kpa	0s 2-12 60s 2-7	ASTM 1667
Shore 00 Hardness		7-30	
Water Absorption	%	-	
Compression Waterseal		>90%	U-TEST
Flammability	Mm/min	<100 >6mm	FMVSS302
Temperature Range	Deg C	-30 / +60	

The above figures are average values.
 We recommend evaluation prior to use to ascertain the suitability of the material for the application.