

Grade

- CBF-1642

Physical

PROPERTY	TYPICAL VALUE
Polymer	SBR/CR
Hardness Shore A	60 (-4 / +5)
Tensile MPa	3
Elongation %	250
Specific Gravity (g/cm ³)	1.5 (+/-0.05)
Minimum Continuous Working Temperature	-20°C
Maximum Continuous Working Temperature	70°C
Maximum Intermittent Working Temperature	90°C
Compression Set 70 Degrees 22 Hours	35% Max

Guidelines for Use

Food Use Suitability	Not Recommended
Abrasion Resistance	Moderate
Ozone weather Resistance	Moderate
Flame Retardency	Moderate
Electrical Resistance	Not Recommended
General Purpose	Good

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any particular application. All data relating to suitable uses and descriptions information concerning our products are compiled from research and are believed to be reliable, but are provided for guidance purposes only. The company holds no legal or contractual responsibility for information supplied.