

Grade: CBF-120

Typical Physical Properties

| PROPERTY | TYPICAL VALUE |
|------------------------------------|--|
| ASTM D1056 (2000) | 2C1/2 |
| Density | 110 – 130 kg m3 |
| Compression Deflection 25% (35-63) | 40 kpa |
| Shore Hardness 00 / C Scale | 40 / 15 |
| Elongation – Minimum | >200% |
| Temperature Range | -30°C / +80°C (+100°C Intermit) |
| Water Absorption | <3% Vol |
| Tensile Strength | 7.4 kg / cm2 |
| Flame Resistance | FMVSS302 UL94 HF1 (Type test only, not officially tested) Self Extinguishing |
| Environmental Protection | CFC & HCFC Free |

The information and data contained herein is believed to be accurate and reliable. However it is the user's responsibility to determine suitability for use. C B Frost & Co makes no warranties concerning fitness or suitability of its products for a particular use or purpose. C B Frost & Co reserve the right to alter the material specification at any time, without prior notice.