

MF775(FR8775)

Test	Result	Report No.	Test Date
Temperature Index (BS EN ISO 4589-3:1996)	341 °C	WF No.151188	10.02.2006
Smoke - BS6853:1999 Annex D.8.3 (Small scale cube)	Ao 0.0162	WF No.151186	10.02.2006
'R' Value - NFX 70-100 (BS6853:1999 Annex B.1)	0.40	WF No.151185	10.02.2006
NFF 16-101 M/I	I2	N0508090	28.08.2012
NFF 16-101 F	F0	N0508090	01.10.2012
EN 45545			
R1 Interiors Primary	HL2(2mm)		
R6	HL2(2mm)		