

**Grade**

- CBF-C20 Eco

**Description**

Good strength and suitability for minor mechanical applications. Moderately resistant to weathering and oxidation ageing. Resistant to some inorganic salts, acids and ozone. Moderate resistance to petroleum-based products other than aromatic and halogenated hydrocarbons.

**Physical**

PROPERTY	TYPICAL VALUE	TEST METHOD
Polymer	CR/SBR	
Colour	Black	
Quality	Commercial Economy	
Hardness	70 Shore A +/- 5A	ISO 7619-1
Specific Gravity	1.4 g/cm <sup>2</sup>	ISO 2781
Tensile MPa	3.5 N/mm <sup>2</sup>	ISO 37
Elongation	250%	ISO 37
Temperature Range	-20 C / + 80 C	

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any particular application. All data relating to suitable uses and descriptions information concerning our products are compiled from research and are believed to be reliable but are provided for guidance purposes only. The company holds no legal or contractual responsibility for information supplied.

**Convertors and suppliers of die cut gaskets, tape, sheeting, fabrications, machined plastic components, rubber mouldings, extrusions and adhesives.**

