

Information

BISCO® HT-800 medium firm silicone foam embodies the transition in the BISCO Silicone Cellular series from soft and conformable to firm and durable. It simultaneously retains the lightness of a foam while exhibiting enhanced sealing capabilities of a traditional sponge rubber. Patented chemistry and cell structure provide a long-term performance advantage.

Features & Benefits, applicable to all BISCO® Cellular Materials (Foams):

- Temperature independency
- UV/ Ozone resistant
- Rated to most stringent flame standards

† It is FDA compliant in accordance with FDA Regulation 21 CFR 177.2600

Physical Properties

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
Colour		Black, Gray, Red	
Thickness mm (inches)		0.79 - 12.70 (0.031 - 0.500)	See "Width Tolerance" table
Density, kg/m³ (lb./ft³)		352 (22)	300 - 473 (18.7 - 29.5)
Compression Force Deflection, kPa (psi)	ASTM D1056	67 (9.7)	41 - 97 (6 - 14)
Compression Set, %	ASTM D1056 100°C (212°F) / 22 hrs / 50%	2.4	< 5
Water Absorption, %	Internal 2" below water surface / 24hrs / change in weight	0.5	< 5

Specification values in bold are tested on a batch basis.

Further industry specifications tested in tables below.

Flammability Properties

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
Flame Resistance	UL 94 (File E83967)	Meets	V-0
Flame Spread Index (Is)	ASTM E162	Meets	Flaming Mode < 35
Smoke Density (Ds)	ASTM E662	Meets	Flaming Mode, 1.5min, < 100 Flaming Mode, 4.0min, < 200
Burn Length	FMVSS 302	Meets	< 100 mm/min

Convertors and suppliers of die cut gaskets, tape, sheeting, fabrications, machined plastic components, rubber mouldings, extrusions and adhesives.



Thermal Properties

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
Temperature Range, °C (°F)	Internal	-55 to +200 (-67 to +392)	-
Thermal Conductivity, W/m °K	ASTM D518	0.076	-
Low Temperature Flex	ASTM D1056 -55°C (-67°F) / 5 hrs	Pass	-
Low Temperature Brittleness	ASTM D746 -55°C (-67°F) / 3 min	Pass	-

Standard Thickness Tolerances

NOMINAL THICKNESS	TOLERANCE
mm (inches)	mm (inches)
0.79 (0.031)	+ 0.381/0.102 (+ 0.015/-0.004)
1.60 (0.063)	± 0.508 (± 0.020)
2.39 (0.094)	± 0.508 (± 0.020)
3.18 (0.125)	± 0.635 (± 0.025)
4.76 (0.188)	± 0.635 (± 0.025)
6.35 (0.250)	± 0.762 (± 0.030)
9.53 (0.375)	± 1.143 (± 0.045)
12.70 (0.500)	± 1.270 (± 0.050)

Slit Material and Tape (PSA) Width Tolerances

NOMINAL WIDTH	TOLERANCE
mm (inches)	mm (inches)
> 0 - 76 (> 0 - 3)	± 1.60 (± 0.063)
> 76 - 203 (> 3 - 8)	± 2.39 (± 0.094)
> 203 - 305 (> 8 - 12)	± 3.18 (± 0.125)
> 305 - 457 (> 12 - 18)	± 4.78 (± 0.188)
> 457 - 660 (> 18 - 26)	± 5.56 (± 0.219)
> 660 - 914 (> 26 - 36)	+ 25.4/- 0 (+ 1/- 0)

Value Added Offerings

- Adhesive (PSA) lamination
- Slit material/tapes

Specification

- AMS3195

† Statement of FDA compliance is based solely on the following: HT-800 (Gray) silicone foams (i) are compounded and cured under conditions of good manufacturing practice; and (ii) have been subjected to annual extraction testing in accordance with FDA Regulation 21 CFR 177.2600 paragraphs (e) and (f) and found to meet all extractives limitations, both of which are criteria set forth in 21 CFR 177.2600 as necessary for rubber articles intended for repeated use in those areas specified in the regulation.

Notes:

- *Typical value – Value is based on historical data. Please note the frequency of testing varies.
- **Specification – Applies to physical properties only, which are based on Rogers' internal benchmark and standard BISCO specification values.

The information given above is based upon average values and is no way intended as a warranty. The purchaser is deemed responsible for determining the suitability of the product for any particular application. All data relating to suitable uses and descriptions information concerning our products are compiled from research and are believed to be reliable, but are provided for guidance purposes only. The company holds no legal or contractual responsibility for information supplied.

t +44 (0) 121 773 8494
f +44 (0) 121 772 3584
w www.cbfrst-rubber.com
e info@cbfrst-rubber.com
t twitter.com/cbfrost



ROGERS
CORPORATION

Convertors and suppliers of die cut gaskets, tape, sheeting, fabrications, machined plastic components, rubber mouldings, extrusions and adhesives.

